

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 2001071203
PUBLICATION DATE : 21-03-01

APPLICATION DATE : 13-08-99
APPLICATION NUMBER : 11229302

APPLICANT : MITSUBISHI MATERIALS CORP;

INVENTOR : UEDA TOSHIAKI;

INT.CL. : B23B 27/14 B23P 15/28 C23C 14/06 C23C 16/30 C23C 16/40

TITLE : SURFACE COATING HARD METAL-MADE CUTTING TOOL EXCELLENT IN SURFACE LUBRICATION RELATING TO CHIP

ABSTRACT : PROBLEM TO BE SOLVED: To improve surface lubrication relating to chips.

SOLUTION: This surface coating hard metal-made cutting tool, formed by chemically evaporating and/or physically evaporating in a mean layer thickness of 3 to 30 μm a hard coating layer constituted by a lower layer of a Ti compound layer consisting of one or two or more kinds of basically layers of TiC, TiN, TiCN, TiCO, or TiCNO and an upper layer of Al₂O₃ layer on a surface of a WC group sintered hard metal base body, has a mean layer thickness of 0.1 to 3 μm thickness as the most surface bedding layer in addition to the hard coating layer. In the case of representing by compositional formula TiO_v, the tool has a Ti oxide layer satisfying V: 1.2 to 1.7 by atomic ratio relating to Ti and a mean layer thickness of 0.05 to 2 μm similarly as the most surface layer, and in the case of representing by compositional formula TiC_xN_y(O)_z (where (O) represents diffusion oxygen from the most surface bedding layer) the tool is formed by chemically evaporating and/or physically evaporating a Ti carbonitroxide layer satisfying X: 0.25 to 0.65, Y: 0.25 to 0.65, z: 0.01 to 0.4, x+y+z=1 by atomic ratio respectively relating to Ti.

COPYRIGHT: (C)2001,JPO